

Unsaturated polyester

Grades	Appearance	SP.GR25C	ViscosityAt25C FC4/second	AcidNo mgkoh/g	Gel time 25Cminut	Styrene content per sent	type	Suggested Application
100	Clear	1.11	100	23-25	10-15	37	Orthophthalic	general purpos
IK101	Clear	1.129	81	22.9	11	38	Orthophthalic	Corrugated sheets&hand lay up
IK110	Clear	1.130-1.150	100	23	10-15	36-38	Orthophthalic	Corrugated sheets&general purpose rooflight rodcasting buttom
IK111	Clear	1.10-1.20	70-90	22-24	8-14	36-38	Orthophthalic	Corrugated sheets
IK121	Clear	1.12-1.17	85	21.4	10.5	37	Orthophthalic	General purpose&Corrugated sheets profiles moulding&light domes
IK121Button	Clear	1.154	160	22.94	7.5	34	Orthophthalic	Button&rod casting
IK125	Clear	1.10-1.16	95	23.1	8.5	34	Orthophthalic	G.R.P products&artificial marble
IK131	Clear	1.12-1.20	85	18.6	13	40	Orthophthalic	Hand lay up
IK300	Clear	1.125	80	19	13.5	38	Orthophthalic	Automobile parts bodies
IK360	Clear	1.131	85	20.6	10	37	Orthophthalic	Statue
IK550	Clear	1.122	110	25.3	11	34	Isophthalic	Good resistance chemicale&good mechanical properties
IK800	Clear	1.093	45	28.3	10	40	Orthophthalic	Polishable wood coating
IK1071	Clear	1.13	80-90	18-19	12-15	36-38	Orthophthalic	G.R.P automobile parts bodies High press mouldings

IK5000	Clear	1.083	39	22.3	12.5	34.5		Glossy wood coating
IK6000	Clear	1.137	125	17.5	11	30		Car body putty
IK7000	Clear	1.10-1.20	30	24.8	9.7	33		R.T.M electrical casting
IK8000	Clear	1.14-1.24	95	25.3	12	35		Marble joint
IK8020	Clear	1.10-1.20	90-100	23-27	2-4	37-36		Marble &Stone joints
IK9000	Clear	1.07-1.15	39	24-25	12.5	35		Low viscosity past mastic paste
IK9050	Clear	1.10-1.18	38-41	24-25	1015	32		Mastic paste
IK20000	Clear	1.15-1.25	100	11.5	10	36		G.R.P products&tank