

Short Oil Alkyds

Ref	Solvent	%NV \pm 1	Gardner Color Max	Acid Value. Max. On solid	Brookfield Viscosity 25 °C poises	Type Of oil	Oil %	Principal properties and main applications
1510	Xylene Aromate solvent	60	6	6-10	250-290	Soya bean	32	Stoving primers and nitrocellulose sealers for wood.
1560	Xylene	60	6	6-10	160-200	Sun flower	33	Stoving enamels in combination with urea and melamine formaldehyde resins.
1565	Xylene	60	6	6-10	160-200	Soya Bean	33	Stoving primers and enamels with good metal adhesion.
1570	Xylene	60	6	6-10	100-140	Coconut	31	Nitrocellulose industrial enamels with good metal adhesion.
1580	Xylene	60	6	6-10	25-46	Soya bean	34	Quick drying industrial paints stove dried enamels in combination with amino resins.